

PRODUCT DATA SHEET

ITEM CODE: SEE DN
ISSUE DATE: 04/07/2025
REVIEW: NO. 3

2000 PLUS B_{ROOF} T2

DESCRIPTION OF THE PRODUCT

Water-based, coloured, liquid elastomeric protective membrane, formulated with special fillers and additives, resistant to standing water and ideal for application on large surfaces. Its reaction to external fire ensures optimal protection of **B_{ROOF} T2** bituminous membranes while providing a certified waterproofing system.

Formulated by WINKLER Research & Development Laboratories.

APPLICABLE REGULATIONS

2000 PLUS B_{ROOF} T2 complies with the following standards and classifications:

- Classified BROOF (T2) in accordance with UNI EN 13501-5 (reaction to external fire)

FIELDS OF USE

2000 PLUS B_{ROOF} T2 is designed for the protection of certified B_{ROOF} (T2) bituminous membranes in applications requiring specific reaction-to-fire performance.

SURFACE PREPARATION

Thoroughly clean the substrate to remove dust, loose or friable material, and any foreign or non-adherent substances. Ensure that the bituminous membranes have been correctly installed and that all overlaps are properly bonded. Repair any damaged or incomplete seals using **WINSEAL**.

RECOMMENDATIONS

- Do not add any additives.
- Do not use the product if the packaging is damaged.
- Do not dilute with water or solvents.

WARNINGS

Apply **2000 PLUS B_{ROOF} T2** at temperatures between +5°C and +35°C. Protect the treated surface from water, rain, and snow for the first 24 hours. Avoid application under conditions of high night-time humidity.

PRODUCT DATA SHEET

PRIMER APPLICATION

If the bituminous membrane on which **2000 PLUS B_{ROOF} T2** is to be applied is not yet oxidized (\leq 180 days), apply **2000 FAST PRIMER** to a clean, dry substrate in a single coat, at a consumption rate of 250 g/m².

Refer to the table below for the recommended waiting time before over-applying **2000 PLUS B_{ROOF} T2**.

TABLE 1 – DRYING TIME 2000 FAST PRIMER

WHEATHER CONDITIONS	OVER-APPLYING
20°C up to 55% RH	3 h
15°C up to 55% RH	5 h
10°C up to 55% RH	8 h
5°C up to 55% RH	12 h

APPLICATION

The product is ready to use. Before application, mix briefly to ensure uniform consistency. Apply on a clean, dry surface using a roller, brush, or airless spray gun.

Apply **2000 PLUS B_{ROOF} T2** in two layers, allowing at least 24 hours between the first and the second coat.

CONSUMPTION

1.2 – 1.4 kg/m² in two coats

PACKAGING

5-10-20 kg buckets

PRODUCT DATA SHEET

STORAGE

The product in its original and undamaged packaging, can be stored for up to 12 months. Store at temperatures between +5°C and 35 °C. The product is not frost-resistant.

SAFETY INSTRUCTIONS

PRECAUTIONS

For safety information, the user must refer to the latest Safety Data Sheet (SDS), prepared in accordance with applicable regulations. The SDS contains detailed information on the physical, toxicological, and safety characteristics of the product.

DISPOSAL AND ENVIRONMENTAL PRECAUTIONS

Do not release the product or empty containers into the environment. For detailed disposal instructions, refer to the most recent Safety Data Sheet (SDS).

TECHNICAL FEATURES (average value)

FEATURES	STANDARD	RESULT
Appearance	-	Fluid Paste
Colour	-	White – Grey – Red - Green
Density at +20°C	EN ISO 2811-1	1,5 ± 0,05 g/cm ³
Solid content	EN ISO 3251	72 ± 2%
pH	UNI EN 8490-4	9 ± 1
Brookfield viscosity at 20°C	UNI EN 8490	20.000 + 2.000 cPs

PRODUCT DATA SHEET

PERFORMANCE OF THE PRODUCT IN SERVICE

FEATURES	STANDARD	RESULT
Operating Temperature	-	-20°C to + 80°C
Initial Elongation at Break	ASTM D 2370	≥ 150 %
Initial Tensile Strength	ASTM D 2370	≥ 2,8 N/mm ²
Accelerated Weathering (5 years)	UNI EN ISO 4892-3 Cycle 3	No delamination or breakage
Elongation at Break after Accelerated Weathering	ASTM D 2370	≥ 100 %
Tensile Strength after Accelerated Weathering	ASTM D 2370	≥ 2,0 N/mm ²
Water Absorption after 7 Days Immersion	ASTM D 471	≤ 20%
Resistance to Ponding Water	-	Excellent

DISCLAIMER AND LEGAL NOTICE – WINKLER

The information and instructions contained in this Technical Data Sheet are prepared on the basis of WINKLER's best technical and application knowledge and are provided for guidance only. However, since WINKLER cannot directly control site conditions or the execution of works, these indications are in no way binding on WINKLER.

The data provided do not exempt the purchaser from the responsibility of verifying, through practical tests and comprehensive applications, the suitability of the product for the intended use and of determining whether it is appropriate for the desired application; the user assumes all responsibility arising from its use. The customer is also responsible for verifying that this Technical Data Sheet is valid for the batch of product of interest and that it has not been superseded by later editions. The updated Technical Data Sheet is available on WINKLER's official website.

The contents of this Technical Data Sheet may be reproduced in other project documents, but the resulting document may under no circumstances replace or supplement the Technical Data Sheet in force at the time of application of the WINKLER product. Any alteration of the text or conditions contained in this Technical Data Sheet or derived from it releases WINKLER from any liability. WINKLER reserves the right to make technical changes of any kind to its products and/or Technical Data Sheets without notice. This revision cancels and replaces all previous ones.