


# PRODUCT DATA SHEET

## ROYAL EXTRA

ITEM CODE: SEE DN  
ISSUE DATE: 5/06/2023  
REVIEW: NO. 5



### DESCRIPTION OF THE PRODUCT

Improved cementitious tile adhesive designed for indoor and outdoor installation of ceramic and grès tiles on both floors and walls.

Classified according to **UNI EN 12004 (C2TE)**: improved cementitious adhesive with additional performance characteristics, reduced slip, and extended open time.

Developed by WINKLER Research & Development Laboratories.

### FIELDS OF USE

Ready-mixed product with high adhesive strength, suitable for installation on floors, heated floors, and wall coverings, both indoors and outdoors.

### SURFACE PREPARATION

Verify that the substrate is sound, properly cured, free from cracks, and compliant with the requirements specified in the **UNI EN 11493-1** standard. Thoroughly clean the surface to ensure it is free from salts, oils, grease, loose particles, and any foreign or non-adherent substances.

### WARNING

Do not add cement or any additives.

Do not use the product if the packaging is damaged.

Do not add water once the mix has begun to set.

### PRECAUTIONS

For existing coatings or surfaces with low wettability, use **WINGRIP NEXT** as an adhesion promoter. For the design, installation, and maintenance of floors using **ROYAL EXTRA**, refer to the provisions of **UNI EN 11493-1**. Apply at temperatures between +5°C and +35°C.

## APPLICATION

Mix thoroughly with clean water (5-5.25 L per bag) until a smooth, homogenous mixture is obtained. Apply the product with a notched trowel. If improved elasticity is required, add 10-15% **ADEGUM LATEX** to the mixing water, adjusting the water quantity accordingly to achieve the desired consistency.

For large-sized coverings (with a surface area greater than 900 cm<sup>2</sup>), or when a full-bed application is required according to **UNI EN 11493-1**, apply **ROYAL EXTRA** using the double-spreading technique – applying the adhesive both to the substrate and to the back of the covering. This ensures full contact and greater mechanical strength.

## CONSUMPTION

3 -3.5 kg/m<sup>2</sup>

## PACKAGING

25 kg bags

## STORAGE

The product in its original and undamaged packaging, can be stored for up to 12 months. Store at temperatures between +5°C and 35 °C. The product is not frost-resistant.

## SAFETY INSTRUCTIONS

### PRECAUTIONS

For safety information, the user must refer to the latest Safety Data Sheet (SDS), prepared in accordance with applicable regulations. The SDS contains detailed information on the physical, toxicological, and safety characteristics of the product.

### DISPOSAL AND ENVIRONMENTAL PRECAUTIONS

Do not release the product or empty containers into the environment. For detailed disposal instructions, refer to the most recent Safety Data Sheet (SDS).

## TECHNICAL FEATURES (average value)

FEATURES	RESULTS
Appearance	Powder
Colour	White – Grey
Specific weight	$1.6 \pm 0.05 \text{ g/cm}^3$
Recommended Mixing Water	5-5.25 lt per bag 20-21%

## CERTIFIED RESISTANCES OF THE PRODUCT IN OPERATION According to UNI EN12004

Extended Open Time: Tensile Adhesive Strength (UNI EN 1346)	After 5 minutes	After 10 minutes	After 20 minutes	After 30 minutes
	$\geq 1.07 \text{ N/mm}^2$	$\geq 1.06 \text{ N/mm}^2$	$\geq 0.51 \text{ N/mm}^2$	$\geq 0.50 \text{ N/mm}^2$
<b>Tensile adhesive strength (UNI EN 1348)</b>				
<b>Initial</b>	$\geq 1.23 \text{ N/mm}^2$			
<b>After thermal aging</b>	$\geq 1.04 \text{ N/mm}^2$			
<b>After water immersion</b>	$\geq 1.03 \text{ N/mm}^2$			
<b>After freeze-thaw cycles</b>	$\geq 1.05 \text{ N/mm}^2$			
<b>Slip resistance (UNI EN 1908)</b>	$\leq 0.5 \text{ mm}$			

## VOLATILE ORGANIC COMPOUNDS EMISSION

Parameter	Max. allowed concentration ( $\mu\text{g}/\text{m}^3$ )
TVOC after 3 days	$\leq 750$
TVOC after 28 days	$\leq 60$

Test performed by the EUROFINS Institute according to EN 16516, ISO 16000-3/6/9/11 and ASTM D5116-10. Test report n. 392-2017-00404102\_G\_EN\_02.

The product complies with the requirements of Directive 2003/53/EC.

### DISCLAIMER AND LEGAL NOTICE – WINKLER

The information and instructions contained in this Technical Data Sheet are prepared on the basis of WINKLER's best technical and application knowledge and are provided for guidance only. However, since WINKLER cannot directly control site conditions or the execution of works, these indications are in no way binding on WINKLER.

The data provided do not exempt the purchaser from the responsibility of verifying, through practical tests and comprehensive applications, the suitability of the product for the intended use and of determining whether it is appropriate for the desired application; the user assumes all responsibility arising from its use. The customer is also responsible for verifying that this Technical Data Sheet is valid for the batch of product of interest and that it has not been superseded by later editions. The updated Technical Data Sheet is available on WINKLER's official website.

The contents of this Technical Data Sheet may be reproduced in other project documents, but the resulting document may under no circumstances replace or supplement the Technical Data Sheet in force at the time of application of the WINKLER product. Any alteration of the text or conditions contained in this Technical Data Sheet or derived from it releases WINKLER from any liability. WINKLER reserves the right to make technical changes of any kind to its products and/or Technical Data Sheets without notice. This revision cancels and replaces all previous ones.