PRODUCT DATA SHEET

ITEM CODE: SEE DN
ISSUE DATE: 06/12/2025
REVIEW: NO. 6

CE

WF05 - RASOSAN

COMPLYING WITH THE UE RULE
UNI EN 998-1
R
RESTORATION MORTAR

DESCRIPTION OF THE PRODUCT

Dehumidifying and breathable skim coat based on hydraulic binders, enhanced with special additives and fillers to promote porosity while maintaining excellent breathability. Formulated by WINKLER Research & Development Laboratories.

FIELDS OF USE

Used in restoration cycles on surfaces affected by rising damp, the product can also serve as a levelling coat in **WF03-WINTOSAN** applications or over other cement- or lime-based plasters.

SURFACE PREPARATION

Thoroughly clean the surface to remove salts, grease, oils, and substances that could impair adhesion.

WARNING

Do not add cements or any additives.
Do not use the product if the packaging is damaged.
Do not add water once the mixture has begun to harden.
Do not apply on asphalt or bitumen-treated surfaces.

PRECAUTIONS

Apply the product at temperatures between +5°C and +35°C. During the first 24 hours, protect the surface from direct sun and wind, and if necessary, continue to keep it damp after application. Store the product before use in a frost-free environment, protected from moisture. Mix the product with cold water. Fresh mortar can be removed from tools used for preparation and application with running water, while hardened material must be removed mechanically.

APPLICATION

Mix thoroughly with 5.8 L (maximum 6.20 L) of clean water per bag until a homogeneous paste is obtained. The product can be applied using a trowel, spatula, or air- spray gun and finished with a wooden trowel.

Winkler Srl
Via M. Buonarroti, 15 - 20093 Cologno Monzese (Mi) - Italy
Tel. +39 02 26 700 605
info@winklerchimica.com - www.winklerchimica.com

CE

CONSUMPTION
1.1 kg/m^2 per mm of thickness

PACKAGING
25 kg bags

STORAGE
The product in its original and undamaged packaging, can be stored for up to 12 months. Store at temperatures between +5°C and 35 °C. The product is not frost-resistant.

SAFETY INSTRUCTIONS

PRECAUTIONS
For safety information, the user must refer to the latest Safety Data Sheet (SDS), prepared in accordance with applicable regulations. The SDS contains detailed information on the physical, toxicological, and safety characteristics of the product.

DISPOSAL AND ENVIRONMENTAL PRECAUTIONS
Do not release the product or empty containers into the environment. For detailed disposal instructions, refer to the most recent Safety Data Sheet (SDS).

Winkler Srl
Via M. Buonarroti, 15 - 20093 Cologno Monzese (Mi) - Italy
Tel. +39 02 26 700 605
info@winklerchimica.com - www.winklerchimica.com

PRODUCT DATA SHEET

CE

TECHNICAL FEATURES
(average values)

WF05-RASOSAN complies with the requirements of **EN 998-1** ("Guaranteed performance mortar with high porosity and reduced capillary action, suitable for restoring damp masonry walls") and fulfils the minimum requirements for classification as **(R)** Restoration Mortar.

FEATURES	STANDARD	RESULTS
Maximum aggregate particle size	-	0.5 mm
Appearance	-	Powder
Colour	-	Light grey
Water for mixture (per 25kg bag)	-	5.8 L (max. 6.2 L)
Mixture specific weight	UNI EN 1015-6	1150 kg/m^3
Mixture porosity	UNI EN 1015-7	>20%

PRODUCT PERFORMANCES
ACCORDING TO UNI EN 998-1

FEATURES	STANDARD	RESULTS
Compressive strength	UNI EN 1015-11	9 N/mm^2 (Class CS II)
Adhesion	UNI EN 1015-12	≥ 0.40 N/mm^2 (Break type: B)
Water absorption by capillarity	UNI EN 1015-18	≥ 3.1 Kg/m^3 (water infiltration ≤ 5mm)
Water vapor permeability μ	UNI EN 1015-19	≤ 15
Thermal conductivity λ	UNI EN 1745	0.70 W/m.K
Reaction to fire	UNI EN 13501-1	A1

Winkler Srl
Via M. Buonarroti, 15 - 20093 Cologno Monzese (Mi) - Italy
Tel. +39 02 26 700 605
info@winklerchimica.com - www.winklerchimica.com

PRODUCT DATA SHEET

CE

VOLATILE ORGANIC COMPOUNDS EMISSION

PARAMETER	MAX. ALLOWED CONCENTRATION (µg/m³)
TVOC after 3 days	≤ 750
TVOC after 28 days	≤ 60

Test performed by the EUROFINS Institute according to EN 16516, ISO 16000-3/6/9/11 and ASTM D5116-10. Test report n. 392-2017-00404102_G_EN_02.

The product complies with the requirements of Directive 2003/53/EC.

PRODUCT FOR PROFESSIONAL USE ONLY

DISCLAIMER AND LEGAL NOTICE – WINKLER

The information and instructions contained in this Technical Data Sheet are prepared on the basis of WINKLER's best technical and application knowledge and are provided for guidance only. However, since WINKLER cannot directly control site conditions or the execution of works, these indications are in no way binding on WINKLER.

The data provided do not exempt the purchaser from the responsibility of verifying, through practical tests and comprehensive applications, the suitability of the product for the intended use and of determining whether it is appropriate for the desired application; the user assumes all responsibility arising from its use. The customer is also responsible for verifying that this Technical Data Sheet is valid for the batch of product of interest and that it has not been superseded by later editions. The updated Technical Data Sheet is available on WINKLER's official website.

The contents of this Technical Data Sheet may be reproduced in other project documents, but the resulting document may under no circumstances replace or supplement the Technical Data Sheet in force at the time of application of the WINKLER product. Any alteration of the text or conditions contained in this Technical Data Sheet or derived from it releases WINKLER from any liability. WINKLER reserves the right to make technical changes of any kind to its products and/or Technical Data Sheets without notice. This revision cancels and replaces all previous ones.

winkler® Advanced Building Material

Winkler Srl
Via M. Buonarroti, 15 - 20093 Cologno Monzese (Mi) - Italy
Tel. +39 02 26 700 605
info@winklerchimica.com - www.winklerchimica.com