PRODUCT DATA SHEET

ITEM CODE: SEE DN
ISSUE DATE: 03/02/2026
REVIEW: NO. 1

CE

WINLIVEL RAPID

COMPLIANT WITH EU NORM
UNI EN 13813
CT C35 F7 B2,0 $A1_{fl}$
SCREEDS AND SCREEDS MATERIAL

DESCRIPTION OF THE PRODUCT

Self-levelling, fast-curing, premixed product formulated with special binders and selected mineral fillers for indoor and outdoor applications, including use at low temperatures. Developed by WINKLER Research & Development Laboratories.

FIELDS OF USE

WINLIVEL RAPID is used for levelling floors with irregularities ranging from 1 to 20 mm including screeds or existing floors. Within a few hours, it develops a smooth and solid surface suitable for the installation of ceramic tiles, marble, terracotta, stoneware, parquet, resilient flooring, or liquid membranes from the WINKLER range. It is ideal in situations requiring rapid over-application and fast floor setting. **WINLIVEL RAPID** can also be applied at low temperatures (≥ 2°C).

SURFACE PREPARATION

Thoroughly clean the substrate to remove salts, oils, grease, loose or friable materials, and substances that could impair adhesion. Soak absorbent substrates with water before application. For ceramic or low-wettability coatings, apply **WINGRIP NEXT** as an adhesion promoter prior to the application of **WINLIVER RAPID**.

WARNING

Do not add cement or any additives.
Do not use the product if the packaging is damaged.
Do not add water once the mixture has begun to harden.
Do not apply on asphalt or bitumen-treated surfaces.

PRECAUTIONS

For wood, parquet, and other coatings sensitive to humidity, apply WINLIVEL RAPID with a minimum thickness of 5 mm. It is also recommended to verify, using a carbide hygrometer, that the residual humidity of the substrate is ≤ 2% before proceeding with over-application. Apply the product at temperatures between +2°C and +35°C. Protect the surface from direct sunlight and wind during the first 24 hours; if necessary, keep the surface slightly moistened even after application. Remove fresh mortar from tools used for preparation and application with running water. Once hardened, the material can be only removed mechanically.

Winkler Srl
Via M. Buonarroti, 15 - 20093 Cologno Monzese (Mi) - Italy
Tel. +39 02 26 700 605
info@winklerchimica.com - www.winklerchimica.com

APPLICATION

Mix the product with clen water until a perfectly homogeneous and lump-free mixture is obtained. To promote adhesion to the substrate, apply the product using a spatula, exerting slight pressure on the surface. While the product is still wet, use a spiked roller to eliminate any air bubbles and ensure a smooth, even finish.

Joints

During application, respect all existing joints in the substrate. It is recommended to separate **WINLIVEL RAPID** from walls and all emerging vertical elements. For the design, sizing, and construction of joints, refer to the provisions of **UNI EN 11493-1**.

Drying times

After 3 hours (at 20°C): acquires sufficient mechanical strength to be walkable
After 4 hours (at 20°C): possible to overlay ceramic floors and liquid membranes
After 7 days (at 20°C): suitable for overlaying stone materials, linoleum, wood, and parquet.

CONSUMPTION

2 kg/m^2 per mm of thickness

PACKAGING

25 kg bags

STORAGE

The product in its original and undamaged packaging, can be stored for up to 12 months. Store at temperatures between +5°C and 35 °C. The product is not frost-resistant.

winkler® Advanced Building Material

Winkler Srl
Via M. Buonarroti, 15 - 20093 Cologno Monzese (Mi) - Italy
Tel. +39 02 26 700 605
info@winklerchimica.com - www.winklerchimica.com

CE

SAFETY INSTRUCTIONS

PRECAUTIONS

For safety information, the user must refer to the latest Safety Data Sheet (SDS), prepared in accordance with applicable regulations. The SDS contains detailed information on the physical, toxicological, and safety characteristics of the product.

DISPOSAL AND ENVIRONMENTAL PRECAUTIONS

Do not release the product or empty containers into the environment. For detailed disposal instructions, refer to the most recent Safety Data Sheet (SDS).

TECHNICAL FEATURES
(average values)

WINLIVEL RAPID complies with the requirements of **UNI EN 13813** ("Screed materials"), particularly for the smoothing of uneven substrates.

FEATURES	RESULTS
Appearance	Powder
Colour	Beige
Water required per 25 kg bag	5.25 l (21%)
Density of the mixture (UNI EN 1015/6)	2.05 ± 0.05 Kg/m^3
Reaction to fire (UNI EN 13501-1)	A 1 $_{fl}$
Pot life at 20°C	40-45 minutes
Setting time at 20°C	70 minutes

Winkler Srl
Via M. Buonarroti, 15 - 20093 Cologno Monzese (Mi) - Italy
Tel. +39 02 26 700 605
info@winklerchimica.com - www.winklerchimica.com

PRODUCT DATA SHEET

CE

PERFORMANCE OF THE PRODUCT ACCORDING TO UNI EN 13813

FEATURES	STANDARD	RESULTS
Compressive strength at 28 days	UNI EN 13892-2	> 35 N/mm²
Flexural strength at 28 days	UNI EN 13892-2	≥ 7.0 N/mm²
Adhesion to concrete	UNI EN 13892-8	> 2.0 N/mm²

VOLATILE ORGANIC COMPOUNDS EMISSION

PARAMETER	MAX. ALLOWED CONCENTRATION (µg/m³)
TVOC after 3 days	≤ 750
TVOC after 28 days	≤ 60

Test performed by the EUROFINS Institute according to EN 16516, ISO 16000-3/6/9/11 and ASTM D5116-10. Test report n. 392-2017-00404102_G_EN_02.

The product complies with the requirements of Directive 2003/53/EC.

PRODUCT FOR PROFESSIONAL USE ONLY

DISCLAIMER AND LEGAL NOTICE – WINKLER

The information and instructions contained in this Technical Data Sheet are prepared on the basis of WINKLER's best technical and application knowledge and are provided for guidance only. However, since WINKLER cannot directly control site conditions or the execution of works, these indications are in no way binding on WINKLER.

The data provided do not exempt the purchaser from the responsibility of verifying, through practical tests and comprehensive applications, the suitability of the product for the intended use and of determining whether it is appropriate for the desired application; the user assumes all responsibility arising from its use. The customer is also responsible for verifying that this Technical Data Sheet is valid for the batch of product of interest and that it has not been superseded by later editions. The updated Technical Data Sheet is available on WINKLER's official website.

The contents of this Technical Data Sheet may be reproduced in other project documents, but the resulting document may under no circumstances replace or supplement the Technical Data Sheet in force at the time of application of the WINKLER product. Any alteration of the text or conditions contained in this Technical Data Sheet or derived from it releases WINKLER from any liability. WINKLER reserves the right to make technical changes of any kind to its products and/or Technical Data Sheets without notice. This revision cancels and replaces all previous ones.

winkler® Advanced Building Material

Winkler Srl
Via M. Buonarroti, 15 - 20093 Cologno Monzese (Mi) - Italy
Tel. +39 02 26 700 605
info@winklerchimica.com - www.winklerchimica.com